

# SurTec® 784

## Drying Additive

### Properties

- liquid
- free of inorganic salts
- low make-up concentration
- non-hydrophobic
- also applicable for stainless steel and electroplated surfaces

### Application

SurTec 784 is used as an additive in the last rinse to give a better drying performance. To receive a spotless surface, SurTec 784 should be dosed in deionised or distilled water. The effect can be improved by increased temperatures.

make-up value: 1-3 l/m<sup>3</sup> (= 0.1-0.3 %vol)

temperature: room temperature up to 90°C

application time: 30-120 s

### Technical Specification

(at 20°C)	Appearance	Density (g/ml)	pH-value (conc.)
SurTec 784	liquid, colourless-yellowish	1.015 (1.0-1.03)	approx. 7-8

### Ingredients

- nonionic surfactants
- alcohols

### Product Safety and Ecology

The safety instructions and the instructions for environmental protection have to be followed in order to avoid hazards for people and environment. The Material Safety Data Sheets (according to European legislation) contain explicit details for this.

The following hazard designations and classifications into water hazard classes (WHC) have to be taken into account:

<u>product</u>	<u>hazard designation</u>	<u>water hazard class</u>
SurTec 784	-	WHC 2

## **Warranty**

We are responsible for our products in the context of the valid legal regulations. The warranty exclusively accesses for the delivered state of a product. Warranties and claims for damages after the subsequent treatment of our products do not exist. For details please consider our [general terms and conditions](#).

## **Further Information and Contact**

In our forum, you can discuss topics of the surface technology:

<http://forum.SurTec.com/>

If you have any questions concerning the process, please contact your local technical department: <http://SurTec.com/International.html>

21 June 2010/DK, UK